

	<u>Physical Properties</u>	Date	2020. 03. 01
		LOTTE CHEMICAL R&D CENTER 115 Gajeong-book St. Yuseong, Daejeon TEL) 042-879-1261,1262	

PEG-200

HONEOL

General Information

Description

Low Dioxane content
Low Free-EO content

Applications

- Rubber, Resins, Cellulosic materials, Dispersants, Textile and leather, Printing inks

Physical Properties¹

General Properties	Test Method	Unit	Specifications	Remarks
Molecular Weight	LC METHOD	-	190 – 210	
Appearance (25°C)	VISUAL		Liquid	
Color(50°C)	ASTM D 1209	APHA	Max 30	
pH	ISO 4316	-	5.0 – 7.0	
Hydroxyl Value	ASTM D 4252	mgKOH/g	537.0 – 590.0	
Water Contents	ASTM D 1744	wt%	Max 0.20	

Note

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications